Beschichten - Stanzen - Schneider

CMC Klebetechnik GmbH Rudolf-Diesel-Straße 4 Germany - 67227 Frankenthal 0049 (0)6233/872-300

TECHNICAL DATA SHEET

CMC TYPE	26785
Supporting Base	polyethylene (LDPE)
Colour	colourless
Thickness without adhesive in mm	0,100 ± 10 %
Thickness with adhesive in mm	0,140 ± 10 %
Adhesive Properties	
Type of adhesive	acrylic
Adhesive strength in N/10 mm	≥ 3
Thermal Properties	
Maximum temperature in °C	80
Flammability according to IEC 60454-2	flame retardant
Isolation class VDE 0530	Υ
Electrical Properties	
Breakdown voltage VDE 0303 in V _{eff.}	8.500
Mechanical Properties	
Tensile strength in N/10 mm	25 – 30
Elongation at break in %	400 – 600
Other Properties	
	,

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.

03/08