Beschichten - Stanzen - Schneider

CMC Klebetechnik GmbH Rudolf-Diesel-Straße 4 Germany - 67227 Frankenthal 0049 (0)6233/872-300

TECHNICAL DATA SHEET

CMC TYPE	
CMC TYPE	70968
Substrate	Kapton® HN (polyimide)
Colour	brown
Substrate thickness in mm	0.075 ± 12%
Total thickness in mm	0.110 ± 10%
Adhesive Properties	
Type of adhesive	polysiloxane
Adhesive strength in N/cm according to internal method PV 1006-32 (180° peel from steel)	≥ 2
Thermal Properties	
Temperature performance (max.) in °C	180
Short term temperature performance in °C (ca. 1 hour)	350
Insulation class according to IEC 60085	Н
Electrical Properties	
Breakdown voltage based on IEC 60243-1 in $V_{\text{eff.}}$	≥ 10'000
Mechanical Properties	
Tensile strength in N/cm	≥ 120
Elongation at break in %	≥ 60
Other Properties	
Liner	repellent polyester film



Quality guarantee:



Information concerning regulation (EC) No 1907/2006 (REACh): This product contains one or more substances of very high concern (SVHCs) from the candidate list in amounts greater than 0.1% (w/w). A detailed statement can be found here: https://en.cmc.de/page/reach

The product is still REACh compliant i.e. its placing on the market is not restricted.

Registered trademark of DuPont de Nemours

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.

03/18